

Multipurpose Kraft Lightweight Spec 160

End use

Longview's bag and wrapping paper grades are made from highly refined pulp in a variety of basis weights and percentages of recycled fiber content. Our bag and wrapping paper grades are valued for their cleanliness, strength, sustainability and end-use possibilities.

Longview offers a variety of grades featuring different sheet characteristics and recycled fiber content for use in multiple bag and wrapping applications. Our industrial wrapping papers are converted and used for building and construction, automotive parts, interleaving, retail wrapping, void fill or cushioning wrap (used in packing to prevent breakage), and more.

Sustainable solutions. Multiple applications.

Options

Our machine finish kraft paper is available in a variety of basis weights ranging from 28 to 67 lbs/3000 ft².

Compliance

Longview's MF paper is manufactured in compliance with FDA, CONEG and RoHS regulations. Our paper is routinely tested to ensure that strict substance limits are met.

Sustainable

At Longview, our products start from trees, a renewable resource. Our paper is made from virgin wood pulp fiber, recycled fiber, or a combination of the two. Our virgin furnish, a blend of Northern softwoods including Douglas fir, pine, hemlock and spruce, provides superior strength properties in our paper.

<u>Property</u>	<u>Units</u>	<u>Typical Values</u>						<u>Test Method</u>
Substance	lbs. / 3000 ft ²	28	30	33	35	38	40	Nominal
Caliper, single	mils	3.1	3.5	3.9	4.0	4.2	4.5	TAPPI T411
Tensile MD	lbs/inch	21.9	23.1	24.0	25.7	27.8	28.4	ISO 1924-3
Tensile CD	lbs/inch	8.4	9.1	10.4	10.8	13.1	14.3	ISO 1924-3
Tear MD	grams	45	49	56	61	70	78	TAPPI T414
Tear CD	grams	55	59	66	74	82	90	TAPPI T414
Porosity	Sheffield	206	215	218	210	225	233	ISO 5636-3
Burst	psi	23	24	26	28	33	34	TAPPI T403
Moisture	percent	7.0	7.0	7.0	7.1	7.2	7.2	

Laboratory conditions 73.4 °F, 50% RH (ISO 554-1976)